# **SVM Tapped Density Tester**



The ERWEKA SVM has been designed for measuring the tapped volume and tapped density of powders, granules and similar products.

The ERWEKA SVM series is available with one or two glass cylinders and operates according USP method 1 (300 strokes/min; stoke height 15 mm) or USP method 2 (250 strokes/min; stroke height 3 mm) which is equal to Pharm.Eur. and DIN ISO EN 787/11 requirements.

As a special version the SVM 223 operates the first test station according USP method 1 and the second station according USP method 2. The test run time is selectable.

### SVM-121 / 221

ERWEKA Tapped Density Testers are available with one (SVM 121) and two test stations (SVM 221) for measuring the tapped volume and tapped density of powders, granules and similar products. Test parameters can be set in either time (hours/minutes/seconds) or number of strokes.

### SVM-122 / 222

The SVM 122 (with one test station) and SVM 222 (with two test stations) operate according USP method 2 and Pharm.Eur. and DIN ISO EN 787/11 standards in respect of strokes/min. and height of stroke.

SVM 121/221 Technical Details			
1 (SVM 121) or 2 (SVM 221) glass cylinders			
14 mm ± 2 mm, 300 strokes/min. ± 15 accoding to USP method 1			
Membrane function keypad			
Two illuminated LED displays			
Time: 1 sec. to 9 hrs, 59 sec. Revolutions: 1 to 99.999			
130 ± 16 g 240 ± 12 g			
220 ± 44 g 450 ± 10 g  1 280 450 450 450 450 450 450 450 450 450 45			

SVM 122/222 Technical D	Details	
Number of test stations	1 (SVM 122) or 2 (SVM 222) glass cylinders	
Stroke height Storkes / min	3.0 mm ± 0.2mm, 250 strokes/min ± 15. according to USP method 2, EP and DIN ISO EN 787/11	
Keypad	Membrane function keypad	
Display	Two illuminated LED displays	
Pre-selection of test run time	Time: 1 sec. to 9 hrs., 59min., 59 sec. Revolutions: 1 to 99.999	2250
100 ml measuring cylinder Support plate	130 ± 16 g 240 ± 12 g	230 210 190 170
250 ml measuring cylinder Support plate	220 ± 44 g 450 ± 10 g	130 110 90 70 50 30
		-10
	A B A T FRHEIA	

# **SVM 223**

### SVM 223

ERWEKA Tapped Density Testers SVM 223 combines two different methods in one single unit. The first test station operates according to the USP method 1. The second test station operates at the same time according to the USP method 2/EP/DIN ISO EN 787, part 11.

SVM 223Technical Details	
Number of test stations	2, one for USP Method 1 and one for USP Method 2 (Pharm. Eur.)
Stroke height Strokes / min	14 mm ± 2 mm, 300 strokes/ min. ± 15 according to USP method 1 3.0 mm ± 0.2mm, 250 strokes/ min. ± 15 according to USP method 2, EP and DIN ISO EN 787/11
Keypad	Membrane function keypad
Keypad Display	Membrane function keypad Two LED displays
31	71
Display  Pre-selection of test-run	Two LED displays Time: 1 sec. to 9 hrs., 59min.,



All ERWEKA glass cylinders with adapter kit according to USP or EP.

## Options

Glass cylinders, 100ml / 250ml / 500ml

USB printer interface

Qualification tool kit

IQ/OQ documents for SVM

